


Protective Silicone Potting & Encapsulation Materials



Momentive Performance Materials provides leading-edge silicone technologies to help meet performance and productivity challenges in a wide range of automotive and electronic applications.

Momentive's dielectric potting and encapsulation materials are excellent candidates to consider to protect electronic components from moisture and harmful contaminants. These materials help provide stress relief protection to circuits from thermal, vibration, and mechanical stress. Momentive offers a range of materials including one and two part products and specialized grades that can provide thermal conductivity, flame retardancy, and low volatiles.

Key Features

- Temperature resistance
- Low modulus, good dampening properties
- Low viscosity
- Very fast cure
- High dielectric strength
- Self healing gels

Typical Benefits

- Thermal and mechanical stress protection
- Easily flows around components
- Productivity, high outputs
- Reliability
- Probe testable

Potential Applications

- ECU potting
- Air flow mass meter
- Sensor potting
- LED encapsulants

Typical Physical Properties

(selected grades only; please contact us for material selection support)

Product	System (1)	Ratio (w/w)	Cure Time	Color	Type	Viscosity (Pa·s)	Feature
TSE3051	AC, 1K	n.a.	1 h @ 150°C	Clear	Gel	0.7	1 Part - Easy handling
TSE3070	AC, 2K	1:1	0.5 hr @ 70 °C	Clear	Gel	0.8	Excellent vibration damping
TSE3032	AC, 2K	10:1	1 hr @ 100°C	Clear	Rubber	4	Non bonding
TSE3033	AC, 2K	1:1	30 min @ 150°C	Clear	Rubber	1	Self bonding
TSE3331K-EX	AC, 2K	1:1	10 min @ 100°C	Dark grey	Rubber	3	UL94 - V0. Thermal conductive
TSE3251	AC, 1K	n.a.	1 hr @ 150°C	White	Rubber	8.5	1K - Easy handling
TSE3667	CC, 2K	100:8	24 hr @ RT	Dark grey	Rubber	3	Low temp adhesion, UL-94 V-0, good deep section cure
RTV11	CC, 2K	Variable	24 hr @ RT	White	Rubber	11	FDA compliant (2), deep section cure possible
TSE3660	CC, 2K	100:8	24 hr @ RT	Light blue	Rubber	3	Low temp adhesion, good deep section cure, UL-94 HB

(1) AC = Addition Cure, CC = Condensation Cure

(2) Compositionally compliant with the requirements of 21 CFR 177.2600 - Rubber articles intended for repeated use have been found, through testing of a representative sample, to meet the extractives limitations in 21 CFR 177.2600(e) and/or (f). It is the responsibility of the user to determine that the final product complies with the extractive limitations and other requirements of 21 CFR 177.2600 under their specific manufacturing procedures.

Typical properties are average data and are not to be used as or to develop specifications.

MOMENTIVE™
 authorized distributor
 +44 1789 773232
 sales@techsil.co.uk
 www.techsil.co.uk

TECHSIL®
 Unit 34 Bidavon Industrial
 Estate
 Waterloo Road
 Bidford on Avon
 Warwickshire
 B50 4JN, UK

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.
 Copyright 2016, Momentive Performance Materials Inc. All rights reserved.